



Raised Floor Solutions Ltd

Date: 12-Jan-16

Certificate of Mix Design

Site / Project: Jarrom Street, Leicester

Plant: Humberstone Lane

Mix Specifications

Mix	Description	Agg Size	Cement Type	Target Consistence
1	C28/35 PUMP MCC320 W/C0.60	20	CEM I	S4

Mix Design

Type	Materials Source	Dry Weights kg/m ³				
		1	2	3	4	5
CEM I	Cemex - Rugby	320				
0/4	Cemex - Willington	883				
4/20	Cemex - Willington	937				
W/C	Free Water/Cement Ratio	0.58				
% Fines	Fines Content (%)	48%				
Chloride	Chloride Content % by Weight of Cement (%)	0.11				
Alkali	Alkali (kg/m3)	2.55				

Mix design details given are subject to variation both in weight and source, given natural variation in material properties and source availability

Additional Information

Signed: 

Emily Moon
Readymix Technical Sales Support

CEMEX UK Operations Limited

CEMEX House, Evreux Way, Rugby, Warwickshire CV21 2DT, United Kingdom.

Phone: +44 (0) 1788 542111 Fax: +44 (0) 1788 540166

www.cemex.co.uk

Registered in England and Wales: Company Number 658390 Registered Office: CEMEX House, Coldharbour Lane, Thorpe, Egham, Surrey TW20 8TD, United Kingdom.